

Technical Data Sheet



TenCate Multi-light CX

| | |
|-----------------------------|---|
| <u>Reference:</u> | To be determined |
| <u>Composition:</u> | SiC + HPPE backing |
| <u>Finish:</u> | Tencate Rosist |
| <u>Dimensions:</u> | 240 x 320 mm \pm 3mm |
| <u>Thickness:</u> | 23 mm \pm 2 mm |
| <u>Weight:</u> | 1.85 kg \pm 0,1 kg (M size) |
| <u>Shape:</u> | SAPI shapes, 5 sizes (Picture does NOT show the correct/final shape) |
| <u>Level of Protection:</u> | In conjunction with a NIJ II vest (SP+2 vest) <ul style="list-style-type: none">▪ VPAM 7 (7.62 x 51 FMJ & SS109) : 3 shots▪ VPAM 6 (7.62 x 39 MSC) : 3 shots▪ 5.45 x 39 MSC : 3 shots |



Final Qualification in conjunction with this specific vest is still pending

Temperature test: The plate preserves its ballistic properties when tested at -20° and +70°C.

Guarantee period: The plate is expected to preserve its conformity with the specifications for a period of at least 5 years during storage from the date of delivery, provided that:

- The product is stored under dry conditions at normal ambient temperature
- The product is stored vertically
- The product has not been subjected to peak temperature exceeding 80°C
- The product is protected against long term direct exposure to sun light

During use do not sit on the insert and avoid dropping on the floor.
Do a visual inspection of the insert every six-month.